

WHITECHEM PU ADH 317

Rubber Tile and Rubber Rolls Adhesive

1 – DESCRIPTION

Whitechem PU ADH 317 is a two component elastic polyurethane based adhesive system. It is a solvent free adhesive.

2 – PROPERTIES

- Two component
- Excellent bonding to applied surfaces
- Suitable for use in adverse weather conditions
- Solvent free
- No smell
- Flexible
- Durable

3 – APPLICATIONS

- Industrial rubber coatings
- Bonding all types of parquets
- Bonding artificial grass sports ground applications
- Bonding rubber sheets to different surfaces such as; concrete, hardboard, chipboard
- Bonding metal, ceramic, concrete, wood etc.

4 – INSTRUCTIONS

MIXING PROCEDURE: Whitechem PU ADH 317 Part A should be mixed thoroughly with the Whitechem PU ADH 317 Part B in a ratio of 7: 1 by weight. Complete and thorough mixing of the components should be carried out by using a mechanical stirrer, for example a powerful drill with a suitable multi-paddle type mixing head. Mix approximately 2 minutes or until an even colour

achieved. Poorly mixed adhesive will not cure correctly and may result in seam failure.

It can be applied with a notched trowel or a suitable applicator. The cleaning can be done with ethyl acetate, butyl acetate etc.

APPLICATION METHOD: Whitechem PU ADH 317 should not be applied onto a wet substrate as this interferes with curing mechanism and bonding. The application surface must be dust, dirt and oil free. The adhesive will normally have at least a one hour workable time at average seasonal temperatures of 15 – 25 °C , but this time can be considerably extended or reduced at lower or higher working temperatures. It is recommended that use all mixed material in working time of adhesive. Avoid to contact with water in 8-10 hours after application.

5- PACKAGING

24 kg set: Part A -21 kg metal tin, part B – 3 kg metal tin

6- STORAGE AND SHELF LIFE

Can be stored for 12 months when kept original, unopened container and protected from frost. Store it in a cool and dry place between 15-25 °C. Material should be stored in a tightly closed container.

7 – TECHNICAL SPECIFICATIONS

| | |
|--|---|
| Appearance | Beige or any desired color |
| Viscosity (cps) | Self Leveling |
| Density (25 °C) (gr/cm³) | 1,52 (A component) 1,2 (B component) |
| Solids (%) | 100 |
| Mix ratio | 7/1: A/B (by weight) |
| Open time (min) | 30-40 (at 23 °C 50% R.H.) |
| Tack free time (hr) | 1-1,5 |
| Film resistance | Water and heat resistant |
| Covarage (kg/m²) | 0,8-1.0 (1 mm thickness) |

8 - WARNING AND SUGGESTIONS

- Read the MSDS form carefully before using the **WHITECHEM PU ADH 317** product or when a problem is encountered and follow the written instructions.
- Personal protective equipment and full face mask with appropriate filter should be used during application.
- There must be sufficient air circulation in the application area.
- Give empty barrels to authorised hazardous waste collector companies